



















TECHNICAL CHARACTERISTICS

wineo 800

Heterogeneous resilient-flooring to glue - Covering type according to EN ISO 10582

wineo

	wineo 800 wood	wineo 800 wood XL	wineo 800 stone XL	wineo 800 tile L / XL / XXL	wineo 800 craft	
Format	1200 x 180mm	1505 x 235 mm	914.4 x 457.2 mm	457.2 x 457.2 mm 914.4 x 457.2 mm 914.4 x 914.4 mm	457.2 x 457.2 mm 914.4 x 101.6 mm	
Product thickness	2.5 mm	2.5 mm	2.5 mm	2.5 mm	2.5 mm	
Planks, tiles / m² per box	16 / 3.46 m ²	12 / 4.24 m ²	10 / 4.18 m ²	16 / 3.34 m ² 10 / 4.18 m ² 6 / 5.02 m ²	16 / 3.34 m ² 20 / 1.86 m ²	
Boxes / m² per pallet	75 / 259.50 m ²	60 / 254.40 m ²	40 / 167.20 m ²	52 / 173.68 m ² 40 / 167.20 m ² 37 / 185.74 m ²	52 / 173.68 m ² 135 / 251.10 m ²	
Guarantee Extended warranty	25 years for private use according to Windmüller warranty conditions - www.wineo.de + 5 years for laying on PU underlay mat					
Classification						Product composition
 Utilization class 23 EN ISO 10874	Domestic area with intensive usage		1 Surface seal			
 Utilization class 33 EN ISO 10874	Commercial sector with heavy usage		2 Surface texture Various embossings			
 Utilization class 42 EN ISO 10874	Light industry sector with regular usage		3 Wear layer Thickness 0.55 mm			
Wear layer binder content EN ISO 10582	Typ I		4 Design Decor film			
 R10 Anti slip category DIN 51130	R 10		5 Base layer			
 Staining and chemical resistance EN ISO 26987	Good resistance according to the concentration and residence time		6 Backing			
 Light fastness EN ISO 105-B02	Light fastness (procedure 2) ≥ 6		7 Underlay material silentPREMIUM or silentPLUS (available separately)			
 Residual indentation EN ISO 24343-1	≤ 0.1 mm without underlay mat ~ 0.17 mm with silentPREMIUM ~ 0.2 mm with silentPLUS		wood bevelled edge tile bevelled edge			
 Castor chair test ISO 4918	25000 revolutions no damage with rolls type W					
 Thermal resistance EN 12667	≤ 0.015 (m ² K)/W without underlay mat ≤ 0.025 (m ² K)/W with silentPREMIUM or silentPLUS					
 Impact sound reduction EN ISO 16251-1	~ 4 dB without underlay mat ~ 17 dB with silentPREMIUM or silentPLUS					
 Dimensional stability EN ISO 23999	~ 0.15 %					
REACH	free from SVHC substances ≥ 0.1 %					
Disposal	<u>Private:</u> Possible with normal domestic refuse <u>Commercial:</u> Refuse-key-no. AVV 170203					
 Windmüller GmbH Nord-West-Ring 21 D-32832 Augustdorf DOP: 0301010 EN 14041:2004 / AC2006 1658 www.wineo.de						
 <p>ÉMISSIONS DANS L'AIR INTÉRIEUR*</p> <p>Information representative des émissions dans l'air intérieur des substances volatiles présentant un risque de toxicité par inhalation, sur une échelle de classe allant de C (fortes émissions) à A+ (très faibles émissions)</p>			 			

Relevant information:

- Utilization class 42 is not possible in conjunction with silentPREMIUM or silentPLUS.
- R 10 Decor „Heavy Metal“ excluded.
- Underfloor heating: Suitable for all conventional hot water underfloor heating and electrical systems regulated up to a surface temperature of 27° C.
- Cleaning and care: see separate cleaning & care instruction.
- Technical subjects can be changed by Windmüller GmbH.