

EAN 5 905 167 847 077

Product number 15825400000000917

MULTIPROTEC M-BASE GLUE 2,1MMx7M

Material	PU/Mineral + PET
Description	Insulating material for the acoustic use under LVT Design floors (dry back)

LVT

Technical Parameters

Symbol	Parameter	Value		Class	Unit	Norm
T	Thickness	2,1	+/-0,2	[-]	[mm]	EN 823:2013
L	Length	7000	-0% + 5%	[-]	[mm]	EN 822:2013
W	Width	1000	-1% +2,5%	[-]	[mm]	EN 822:2013
Q	Squareness	≤ 4		[-]	[mm/m]	EN 824:2013
S	Flatness	≤ 1		[-]	[mm/m]	EN 825:2013
AW	Surface mass	1,68	+/-10%	[-]	[kg/m ²]	EN ISO 23997:2012
RWS	Reflected walking sound	47	+/-2	[-]	[sone]	CEN/TS 16354:2013, EPLF 021029-3
IS	Impact sound improvement	21/10*	+/-2	[-]	[dB]	EN ISO 10140:2007
CS	Compressive strength at 0.5 mm compression	300	+/- 10%	CS3	[kPa]	EN 826:2013
CC	Static compressive strength	50	+/- 10%	CC3	[kPa]	EN 1606:2013
DL	Dynamic compressive strength	> 2 500 000		DL3	[cycles]	EN 13793:2014
PC	punctual conformability	1,3	+/- 10%	PC2	[mm]	EN ISO 868:2005
TR	Thermal Resistance	0,01	+/- 0,003	[-]	[m ² K/W]	EN 12664:2002
SD	sD-value	>75		[-]	[m]	EN 12086:2013
RLB	Resistance to Large Ball	≤ 1300		RLB3	[mm]	EN 438-2:2016
RTF	Reaction on fire	Bfl-s1		[-]	[-]	EN 13501-1:2010

* system AROQ dry back floor with glue UZIN KE 66

Logistic Parameters

Packaging Unit	Form	Amount +/- 10%		Weight +/- 10%		Sizes	
	Roll	7	[m ²]	12,46	[kg]	155 x 155 x 1060	[mm x mm x mm]
Collective packaging	Form	Amount +/- 10%		Weight +/- 10%		Sizes	
	Palette	280	[m ²]	518,4	[kg]	1200 x 800 x 1200	[mm x mm x mm]
Packaging materials	Amount of Paper +/- 10%		Amount of Foils +/- 10%		Amount Remaining +/- 10%		
	0,7 [kg]		0,006 [kg]		[-] [kg]		
Other	Customs tariff number		Waste key		Recycling		
	39211310		170604		Yes		

Standards and Certificates

EN 16354:2018



The information is based on the current state of knowledge and technological development. The information may not contain comprehensive data and all previous versions of the technical data sheet are no longer valid.

Please send questions to the following email address: Reklamacje@decora.pl

creation date

2022-09-08

modification date

2022-09-08

Printed

08.09.2022 10:21