

Laborbericht B20-075



Lichtreflexionswerte Wineo 1500

Dekor	Charge	Struktur	LRV
warm four	3649-1	S 11	1,6
Napa walnut oak	3592-1	S 75	2,6
supreme oak grey	3612-2	S 75	2,8
pure Three	3547-8	S 13	5,1
crafted oak	3584-4	S 12	6,9
Aves brown	2161-4	S 20	9,2
just concrete	3590-6	S 13	10,8
Pure Four	4749-6	S 13	12,3
Navi Blue Star	2229-3	S 13	13,8
steel grey	4889-6	S 13	16,6
Nobel Elm	2928-1	S 75	17,1
Nussbaum Kirsche	1948-1	S 75	18,5
cool two	3590-1	S 13	20,2
Moonlight chip	1412-7		21,0
Cottage Oak	2233-1	S 75	26,7
summer sky	4708-1	S 13	28,1
Orange	4886-3	S 13	28,8
silver grey	4889-6	S 13	29,4
Canyon Oak	2430-2	S 09	29,7
Warm Three	4748-1	S 13	30,5
beige sheet	4761-1	S 75	33,5
Pacific Oak	1883-2	S 75	39,3
Halifax oak	2640-5	S 75	40,7
Classic Oak Spring	2517-1	S 12	41,4
Natural	4858-1	S 13	45,3
apple green	4888-6	S 13	45,9
light beige	4843-1	S 75	46,4
light grey	4854-1	S 11	46,5
Wood Sand	2231-5	S 13	47,7
dove	4757-2	S 11	51,3
Warm 2	2234-1	S 13	51,6
Warm Two	4750-6	S 13	53,3
Sinai Sand	4695-1	S 75	58,9
Malmoe Pine	1489-8	S 20	60,3
Pure White	4696-1	S 75	82,4